



This comparison test, characterized by monitoring and tracing the generation changes of N-type TOPCon and N-type BC modules across the daytime, low and high irradiance, elevated temperatures, intense and unintended ground reflection, provides an ideal environment to gain critical

